

Test number	Test materials	Sample shapes	Test method	Sample models	Spec code	Temperature	Entry time	Product name	Tester	Auditor	Production date
30683637-12-30	Rubber	Circular	Compression				12/30/2011	Original parts	Test Center		12/30/2011
	Sample number	Sample shapes	Area	Diameter	Maximum force (n)	Compressive strength (MPa)	Yield strength (n)	Yield strength (MPa)	Offset yield strength (n)	Offset yield strength (MPa)	Young's modulus (GPa)
30683637- URO	6	Circular	387.0756	22.2	23111.7	44.86	18219.7	44.56	72.1	0.19	0
30683637- OEM	7	Circular	387.0756	22.2	15583.4	40.26	15539.6	40.15	71.7	0.19	0

STRENGTH TEST

-6
-7

